

JH Rhodes Polishing Pad Product List



20111214

Popular Pad	Pad Properties			Typical Applications															
				Glass						Crystal					Metal		Ceramic		
Pad Type	Filler	Density [g/cm ³ (lb/ft ³)] Average	Hardness (Shore A) Average	General Purpose	Flat Panel Display	Hard Disk Substrate	Precision Optics	Fiber Optics	Plastic Lens	Quartz	Sapphire	Silicon	CMP - Titanium	Zinc Selenide	Stainless Steel	Precious Metals	Alumina	Ferrite	Silicon Carbide
CPC-026	None	0.56 (35)	89				•							•					
ESM-013	None	0.59 (37)	84				•					•							
ESM-U	None	0.70 (44)	95				•					•	•						
GR-35	Zirconium Oxide	0.59 (37)	90	•	•		•	•									•		
LP-13	Cerium Oxide	0.35 (22)	66	•			•			•									
LP-26	Zirconium Oxide	0.58 (36)	88	•	•		•			•				•	•	•			
LP-26D	Diamond	0.56 (35)	87						•										
LP-46	Zirconium Oxide	0.40 (25)	74	•			•	•		•									
LP-57	None	0.51 (32)	88	•			•			•	•		•			•	•		
LP-57C	None	0.53 (33)	88								•								
LP-66	Cerium Oxide	0.42 (26)	78	•	•	•	•	•		•	•				•		•		•
LP-77	Cerium Oxide	0.43 (27)	78	•	•		•			•									
LP-87	None	0.78 (49)	96	•			•				•				•			•	•
LP-88	Cerium Oxide	1.12 (70)	n/a	•			•												
LP-99	Silica	0.43 (27)	80												•			•	•
LP-LASER	Zirconium Oxide	0.58 (36)	90				•												
LP-S	Silica	1.09 (68)	n/a		•									•	•			•	•
M-25	None	0.42 (26)	89								•	•							

JH Rhodes Co., Inc. 4809 East Thistle Landing Drive, Suite 100 Phoenix, Arizona 85044, USA

Specifications subject to change without notice.

Tel. +1-480-346-7064 E-mail: info@jhrhodes.com